**S184 – Vehicle Crossings**

**Temporary Access**

Specification for temporary accesses

150mm Type 1 sub-base to BS EN 13285 (no geotextile), from an approved supplier and non-frost susceptible (frost susceptible acceptable for temporary accesses).
Compacted in line with Clause 7.2.4.5 of BS1377 Part 4.

200mm AC20 binder course 50 pen to BS EN 13108-1. Grade 40/60 to BE EN 12591.
Laid in 2 layers to achieve 2%-8% air voids. Laid in one mat with no joints.
Tack coat K1-60 to BS EN 13808 to be laid between layers.

Levels should be such that water run-off is to the sides of the access or into the site rather than onto the highway.